

Name	Shell	L'guard 6	Mercon SP	Pentosin	Mobil	Havoline	Maxlife
Property	M1375.4			ATF1 LV	Dexron VI	Dexron VI	ATF
Den @ 15°C/59°F	840	840	849	845		846	843
Kin Visc @ 100°C	5.6		5.7	5.6	5.8	6	6
Kin Visc @ 40°C	26.8	26.8	27.3	25.3	29.5	30.6	28.5
Visc Index	151		155	168	145	147	163
Dyn Visc @ -40°C	8500		8610	6800	11500	11700	10600
Pour Point °C	-51	-51	-45	-54		-54	-42
Flash Point °C	210	210	218	>206	220	217	202

Gulf	Castrol	Mercon LV	Mobil-1	Mercon V	Pentosin	Esso
Dexron VI	Dexron VI				ATF1	LT-71141
841	846	842	846	863	850	855
6	6.1	6	7.4	7.5	7.6	7.4
29.8	30.2	29.6	36.3	33.2	38	37
153	148	155	167	205	171	
11500	11000	10200	10040	10000	14000	18000
-51	-54	-48	-51	-48	-51	-54
200	177		220	196	>220	219